


Description:

Double-layer flexible bituminous shingle, with glass fiber carrier and protected by colored ceramic-coated basalt.

Application:

Application on pitched roofs, with a slope between 5° and 85°. Installation temperature above +5°C. Always check the adhesion of the pads or of the shingle at the end of the installation.


GENERAL INFORMATION

	Norm	Unit of Measure	Value	Tolerance
Bitumen Type / Compound Type	-		Oxidized Bitumen	
Length	EN 544	mm	998	±3
Width	EN 544	mm	337	±3
Thickness	-	mm	3,3 / 6,6	±10%
Exposed Area	-	mm	143	-
Nailing Axis Position	-	mm	160 - 180	-
Adhesion System			Self-Adhesive Pads	

PHYSICAL-CHEMICAL PROPERTIES

	Norm	Unit of Measure	Value	Tolerance
Weight (Finished Product)	-	kg/m ²	12,3	±10%
Bitumen per Single Layer	EN 544	g/m ²	>1500	-
Tensile Strength MD/CMD	EN 12311-1	N/50mm	>800 / >600	-
Resistance to Tearing (Nail Shank Method)	EN 12310-1	N	>150	-
Water Absorption	EN 544	%	<1	-
Resistance to UV Radiation	EN 1297	Visual	Pass	-
Resistance to Blistering	EN 544	Visual	Pass	-
Flow Resistance, at 90°C	EN 1110	mm	<1	-
Granules Adhesion	EN 12039	-g	<1,5	-

FIRE BEHAVIOR

	Norm	Unit of Measure	Value	Tolerance
External Fire Resistance	EN 13501-5 / EN 1187		Roof (t1, t2)	
Reaction to Fire	EN 13501-1 / prEN ISO 11925-2		E	

PACKAGING

	Norm	Unit of Measure	Value	Tolerance
Type			Polyethylene Film	
Shingles per Bundle			14	
m ² /Bundle			2,00	
m ² /Pallet			136,00	
Pallet Weight (Standard Packaging)			1520 - 1830	

Safety:

The material is free of asbestos, tar compounds and other dangerous substances.

Storage:

Store pallets in closed warehouses, away from heat sources and direct sunlight. Store in the original packaging. Do not stack pallets.

Other information:

The characteristics expressed refer to the standard production. Tegola Canadese reserves the right to update the technical data sheets without notice. Further information on installation available on www.tegolacanedese.com.

